

NR AGARWAL INDUSTRIES LTD.(UNIT II)

Quality: NR Prima



The mark of responsible forestry

Specification Sheet - M/c Deckle : 387-393 cm

Properties	Units	Tolerance	Values											Standards
			48	50	52	54	56	58	60	68	70	80	100	
Substance	gsm	± 2.5%	48	50	52	54	56	58	60	68	70	80	100	TAPPI T410 om-98
Thickness	µm	± 5%	62	65	68	69	72	74	77	87	90	102	128	TAPPI T411 om-97
Bulk	cm ³ /gm	± 5%	1.30	1.30	1.30	1.28	1.28	1.28	1.28	1.28	1.28	1.28	1.28	-
Moisture	%	± 0.5	5.0	5.0	5.0	5.0	5.0	5.0	5.0	5.0	5.0	5.0	5.0	TAPPI T412 om-94
Cobb ₆₀	TS	Max	24	24	24	24	24	24	24	24	24	24	24	TAPPI T441 om-98
	WS	Max	25	25	25	25	25	25	25	25	25	25	25	TAPPI T441 om-98
Breaking Length	MD	± 200	3500	3500	3500	3500	3500	3500	3500	3500	3500	3500	3500	TAPPI T404 om-92
	CD	± 150	1800	1800	1800	1800	1800	1800	1800	1800	1800	1800	1800	TAPPI T404 om-92
Tear Factor	CD	Min	45	45	45	45	45	45	45	45	45	45	45	TAPPI T414 om-98
Brightness	TS	± 1.0	80	80	80	80	80	80	80	80	80	80	80	ISO 2470
Opacity		Min	88	88	88	88	88	90	90	90	90	93	93	ISO 2471
Smoothness (Bendtsen)	TS	Max	220	220	220	220	220	220	220	220	220	220	220	ISO 8791-2
	WS	Max	280	280	280	280	280	280	280	280	280	280	280	ISO 8791-2
Wax Pick	No.	Min	9A	9A	9A	9A	9A	9A	9A	9A	9A	9A	9A	TAPPI T459 om-93

Features:

- It is uncoated paper made from chemical deinked pulp.
- Good Bulk, shade stability and smoothness.
- Suitable for single color printing jobs.
- Used in making Notebooks, Textbooks, Novels, Examination Material.
- GSM range from 48 to 100

Construction



Deinked Chemical Pulp

Note: 1. All Properties are according to NR Agarwal Industries Ltd Unit-II , Vapi measurements.

2.All Properties climate 50% RH & 23oC (as per TAPPI T 402 sp-98)

3.Tolerances are based upon 2 sigma level of random samples.